

COLOUR FASTNESS VALUES - AATCC Standard																												ARTICLE: YORI REC							
COLOUR		CHLORINATED WATER AATCC 162	LIGHT AATCC 16-20 AFU	WATER 38°C AATCC 107							SEA WATER 38°C AATCC 106							PERSPIRATION AATCC 15							CROCKING AATCC 08		WASHING 49°C AATCC 61-2A								
		C.C.	C.C.	C.C.	AC	CO	PA	PL	PC	WO	C.C.	AC	CO	PA	PL	PC	WO	C.C.	AC	CO	PA	PL	PC	WO	S.CO DRY	S.CO WET	C.C.	AC	CO	PA	PL	PC	WO		
2210	White	3,5	3,5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5		
2819	Black	4,5	4,5	4,5	3,5	4	3	3,5	4	3,5	4,5	3,5	4	3	3,5	4,5	3,5	4,5	4	4,5	4	4,5	4,5	4	4,5	4	4,5	3,5	4	3	3,5	4,5	4		
148126	Marine	4,5	4,5	4,5	3,5	4	3	3,5	4	3,5	4,5	3,5	4	3	3,5	4,5	3,5	4,5	4	4,5	4	4,5	4,5	4	4,5	4	4,5	3,5	4	3	3,5	4,5	4		
3414	Radical Red	4	4	4,5	4	4,5	4	4,5	4,5	4,5	4,5	4	4,5	4	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4	4,5	4	4,5	4,5	4,5		
5715	Deep Purple	4	4,5	4,5	4	4,5	4	4,5	4,5	4	4,5	4	4,5	4	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4	4,5	4,5	3	4	2,5	4	4,5	3,5			
12316	Bright Blue	4	4,5	4,5	4	4,5	4	4,5	4,5	4,5	4,5	4	4,5	4	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4	4,5	3,5	4,5	3	4	4,5	4			
75725	Maroon'	4	4,5	4,5	4	4,5	4	4,5	4,5	4,5	4	4	4,5	4	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4	4	3,5	4	4,5	4			
12216	Sea Blue	4	4,5	4,5	4	4,5	4	4,5	4,5	4,5	4	4	4,5	4	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4	4	4	4	4,5	4			
45029	Charcoal	4	4,5	4,5	4	4,5	4	4,5	4,5	4,5	4	4	4,5	4	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4	4	3,5	4	4,5	4		

Fluorescent Colours - CF to Light AATCC 16-10 AFU'

5815	Magenta	4	4,5	4,5	4	4,5	3,5	4,5	4,5	4	4,5	4	4,5	3,5	4,5	4,5	4	4,5	4,5	4	4,5	4,5	4,5	4	4,5	3,5	4	3	4	4,5	4	
5915	Mauve	3	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4	4,5	3,5	4,5	4,5	4,5
5913	Dusty Pink	2,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4	4,5	4	4,5	4,5	4,5
6213	Coral Bliss	4	4	4,5	4,5	4,5	4	4,5	4,5	4,5	4,5	4	4,5	4	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4,5	4	4,5	4	4,5	4,5	4,5

ARTICLE	515 YORI REC
COMPOSITION	82% RECYCLED POLYESTER 18% SPANDEX
WEIGHT	190 g/m ² - 5,60 oz/yd ²
WIDTH	150 cm - 59"
RCLL LENGTH	70 mt
SAMPLING COLOURS	ALL COLOUR CARD SHADES
STRETCH TO DYNAMOMETER - ASTM D 4964 - Load 20 Nf	
PREPARED FOR PRINTING: (+/-15%)	WIDTH 105% LENGTH 120%
CLOURED: (+/-15%)	WIDTH 115% LENGTH 145%

Width and weight values may vary according to the declared tolerances.

CLOUR CHANGE	C.C.
STAINING ON ACETATE	AC
STAINING ON COTTON	CO
STAINING ON POLYAMIDE	PA
STAINING ON POLYESTER	PL
STAINING ON ACRYLIC	PC
STAINING ON WOOL	WO

LIGHT	ASSESSMENTS	OTHER TESTS	ASSESSMENTS
1	VERY WEAK	1	WEAK
2	WEAK	2	LIMITED
3	MODERATE	3	FAIR
4	FAIR	4	GOOD
5	GOOD	5	EXCELLENT

TEXTILE CARE LABELLING		
SYMBOL	DESCRIPTION OF PROCESS	
	WASHING:	MACHINE WASH AT 40°C
	BLEACHING:	DO NOT USE CHLORINE-BASED BLEACH.
	DRYING:	AVOID SPIN DRY. SQUEEZE OFF EXCESS WATER OR DELICATE SPIN. HANG TO DRY.
	IRONING:	MAXIMUM SOLE-PLATE TEMPERATURE OF 110°C
	DRY CLEANING:	ARTICLES WHICH ARE SUITABLE FOR DRY CLEANING IN PERCHLOROETHYLENE.

