



Hung Yen Knitting & Dyeing Co. Ltd

kira – karima

kira – karima

Features

- Classic nylon charmeuse : 80 % nylon – 20% elastane
- They boast a soft and delicate hand feel, perfect fit, a high shaping power and ensure absolute comfort and freedom of movement
- Both fabrics are highly chlorine resistant thanks to the presence of Creora®highclo™by Hyosung
- They are abrasions resistant
- They are UV protective (UPF50+)
- They have been certified by Reach and OEKO-TEX®
- They were designed for watersports. Kira and Karima are perfect for the creation of swimwear but are also suitable for sportswear

Warnings

Bleeding. Neon shades and turquoise are really sensitive to pH changes. Therefore in case of garments are produced in a highly humid environment, once they are finished, they may display some sort of bluish stains which might be removed by washing the garments. Such colours shall be consequently handled with care.

Colour fastness. Fastness values stated with reference to a given shade when creating the recipe and in the colour card cannot be improved any further. Hung Yen guarantees that all products comply with the stated values, with an allowance by 0.5 points, should such products be tested in other laboratories.






Colour matches. It is not advisable to put together colours with fastness values below 4.5. It is anyway recommendable to test all matches in the lab in order to avoid problems during production.

Applique. All applique, logos, printed patterns (especially those to be applied onto neon shades or turquoise) have to be tested so to assess any possible changes in the colour and select the most suitable process.

Hung Yen Knitting & Dyeing Co. Ltd is responsible for the quality of the fabric before it is manufactured into garments. Therefore we recommend a careful check of the fabric upon its reception

ARTICLE	110 KIRA
COMPOSITION	80% NYLON 20% ELASTANE
WEIGHT	195g/m2 - 5.75 oz/yd2
WIDTH	150cm - 59"
ROLL LENGTH	70mt
SAMPLING COLOURS	ALL COLOUR CARD SHADES
STRETCH TO DYNAMOMETER - ASTM D 4969 - LOAD 20 lbf	
PREPARED FOR PRINTING: (+/-15%)	WIDTH 105% LENGTH 190%
COLOURED: (+/-15%)	WIDTH 110% LENGTH 200%

ARTICLE	210 KARIMA
COMPOSITION	80% NYLON 20% ELASTANE
WEIGHT	175g/m2 - 5.16 oz/yd2
WIDTH	150cm - 59"
ROLL LENGTH	70mt
SAMPLING COLOURS	0210 *1813-0314-0115-5416-0716-0318-0919
STRETCH TO DYNAMOMETER - ASTM D 4969 - LOAD 20 lbf	
PREPARED FOR PRINTING: (+/-15%)	WIDTH 105% LENGTH 170%
COLOURED: (+/-15%)	WIDTH 110% LENGTH 180%

TEXTILE CARE LABELLING		
SYMBOL	DESCRIPTION OF PROCESS	
	WASHING	MACHINE WASH AT 40C
	BLEACHING	DO NOT USE CHLORINE BASED BLEACH
	DRYING	AVOID SPIN DRY, SQUEEZE OF EXCESS WATER OR DELICATE SPIN. HANG TO DRY
	IRONING	MAXIMUM SOLE-PLATE TEMPERATURE OF 110C
	DRY CLEANING	ARTICLES WHICH ARE SUITABLE FOR DRY CLEANING IN PERCHLOROETHYLENE
WIDTH AND WEIGHT VALUES MAY VARY ACCORDING TO THE DECLARED TOLERANCES		

COLOUR CHANGE	C.C.		
STAINING ON ACETATE	AC		
STAINING ON COTTON	CO		
STAINING ON POLYAMIDE	PA		
STAINING ON POLYESTER	PL		
STAINING ON ACRYLIC	PC		
STAINING ON POLYESTER	PL		
STAINING ON WOOL	WO		
LIGHT	ASSESSMENTS	OTHER TESTS	ASSESSMENTS
1	VERY WEAK	1	WEAK
2	WEAK	2	LIMITED
3	MODERATE	3	FAIR
4	FAIR	4	GOOD
5	GOOD	5	EXCELLENT